

Tribol™OG 500-0 Spray

Spray Grease for Open Gears

Description

Castrol Tribol™OG 500-0 Spray with TGOA (previously called Castrol Tribol™ 5000 Spray) is a new, sprayable high-performance open gear grease. It was especially developed for application in cement, mining and other heavy industries, to assure proper tribo-technical and economical maintenance of open gears.

Castrol Tribol OG 500-0 differs from conventional asphaltic type open gear lubricants, as it does not contain solvents nor solids.

Outstanding extreme pressure (EP) antiwear characteristics are derived from the latest development in the field of surface improving additives designated TGOA. The TGOA additive package performs better than other EP and antiwear additives because of its unique action on frictional surfaces.

Castrol Tribol OG 500-0 is approved by major original equipment manufacturers.

Castrol Tribol OG 500-0 is manufactured from mineral oil, selected for optimum physical and chemical stability, blended with special adhesive agents and thickened with aluminum complex soap.

The TGOA additive package is activated by high specific loads and corresponding temperatures causing a chemical physical reaction. This results in an equalization of surface roughness without creating abrasion. Therefore, surface roughnesses are reduced without the loss of surface material.

The results of the TGOA additives can be compared with a rolling process in the micro range. The surface roughnesses are gradually leveled and smoothed.

The load carrying area is increased with increased safety loads on tooth flanks at reduced friction levels.

If, because of shock loads or stop and go operation, surface roughness peaks redevelop, the TGOA additive package is automatically reactivated. Surface roughness is again equalized and lubrication optimized.

Application

- Castrol Tribol OG 500-0 is a high-performance lubricant for open gears, wire ropes and similar applications.
- Castrol Tribol OG 500-0 is recommended for the use on slow moving, heavily loaded open gears.
- It is also used to lubricate rack-and-pinion gears, wire ropes, slides, cams and other machinery in mills and mines and other heavy industries.
- Temperature range: 20°C up to + 120°C, +140°C intermittent.

Conditions of Use

- Castrol Tribol OG 500-0 should not be mixed with greases of a different thickener.
- Relubrication intervals should be adjusted according to operating conditions.

Advantages

- Castrol Tribol OG 500-0 forms a very tough lubricating film on friction surfaces. This stable film offers excellent resistance to high loads even at slow speeds. In the FZG special test for grease (A/2.76/50) Castrol Tribol OG 500-0 reaches a scoring load stage of >12 with an extremely low specific wear of <0.20 mg/kWh.
- Regeneration of damaged frictional surfaces can occur on a microscale range. The lubricant film is resistant to weather and environmental influences.
- The stable protective lubricant film is easily and economically applied through automatic dispensing systems over a wide temperature range: 20°C up to + 120°C, 140°C intermittent.
- Increased life of machinery and lubricants.
- Extended lube intervals, reduced consumption and consequential reduction of maintenance and repair costs.

Typical Characteristics

Name	Method	Units	Tribol OG 500-0 Spray
Thickener	-	-	Aluminium Complex
Worked Penetration (60 strokes @ 25°C / 77°F)	ASTM D217 / ISO 2137	0.1 mm	355 - 385
Copper Corrosion (24 hrs, 100°C / 212°F)	ASTM D4048	Rating	1
Base Oil Viscosity @ 40°C / 104°F	ASTM D445 / ISO 3104	mm ² /s	490
Base Oil Viscosity @ 100°C / 212°F	ASTM D445 / ISO 3104	mm ² /s	32
Water Resistance	DIN 51807-1	Rating	1
FZG Gear Scuffing test - A/2.76/50	ISO 14635-3	Failure Load Stage	>12
Four Ball Wear test - Weld Load	DIN 51350-4A	N	2000/2200

1 mm²/s ^ 1cSt

This product was previously called Tribol 5000 Spray. The name was changed in 2015.

Tribol™OG 500-0 Spray
20 Jan 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

www.castrol.com/industrial