

Product Data

Tribol™ GR 400 PD Range

Long-term Greases with MicroFlux Trans

Description

Castrol Tribol™ GR 400 PD (previously called Olista™ Longtime) is a range of mineral oil based, lithium soap greases enhanced with the MicroFlux Trans (MFT) additive system. They are particularly suited for long-term lubrication and for heavy mechanical loads such as extremely high pressures, vibrations and shock loads.

Application

- For long-term lubrication, even under the most difficult operating conditions such as extreme pressure, vibrations, sloads and a wide temperature range in highly loaded rolling and sliding bearings
- For open gear wheels and worm gears at low speeds
- Tribol GR 400-3 PD (previously called Olista Longtime 3 EP) is especially suited to highly loaded bearings in all are industry
- Temperature application range:
 - o -30°C / 22°F to + 140°C / + 284°F for Tribol GR 400-2 (previously called Olista Longtime 2)
 - \circ -25°C / -13°F to +140°C / +284°F for Tribol GR 400-3 (previously called Olista Longtime 3 EP)

Advantages

Compared to conventional greases, the Tribol GR 400 PD Range provides the following advantages:

- Shortened running-in phase, suited for long term and, in some cases, lifetime lubrication
- Outstanding load bearing capacity
- · Optimum wear protection in the high load range
- Smooths existing surface damage
- Significantly reduced coefficient of friction
- · Age-resistant and shear-stable
- · Resistant to cold and hot water
- Extraordinary adhesion, water and dirt-repellent
- Extended service life of machine elements
- Tribol GR 400-2 PD provides excellent corrosion protection
- Tribol GR 400-3 PD helps to prevent fretting corrosion

As a result of the above advantages, the Tribol GR 400 PD Range can help lower the costs of energy, maintenance and disposal.

Typical Characteristics

Name	Method	Units	GR 400-2 PD	GR 400-3 PD
Colour	Visual	-	Brown	
Base Oil	-	-	Lithium Soap / Mineral Oil	
Worked Penetration (60 strokes @ 25 °C/77 °F)	ISO 2137/ASTM D217	0.1 mm	265 - 295	220 - 250
Worked Penetration (100,000 strokes @ 25 °C/77 °F)	ISO 2137/ASTM D217	0.1 mm	35	30
Dropping Point	ISO 2176/ASTM D566	°C/°F	>180/>356	>185/>365
Water Resistance	DIN 51807-1	Rating	1 - 90	1 - 90
Rust Test - EMCOR (distilled water)	ISO 11007/ASTM D6138	Rating	0	n/a
Copper Corrosion (24 hrs,100 °C/212 °F)	ASTM D4048	Rating	1	1

Subject to usual manufacturing tolerances.

Additional Information

In order to minimise potential incompatibilities when converting to a new grease, all previous lubricant should be removed as much as possible prior to operation.

During initial operation, re-lubrication intervals should be monitored closely to ensure all previous lubricant is purged.

This product was previously called Olista Longtime Range. The name was changed in 2015.

Tribol™ GR 400 PD Range 04 Sep 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.