

Klübersynth BHP 72-102

High-temperature lubricant with extraordinary anticorrosion properties for lifetime lubrication



Benefits for your application

- **Long availability of components over a wide service temperature range**
 - when exposed to corrosive atmosphere
 - when exposed to high vibrations and loads
- **High economic efficiency due to innovative hybrid grease formulation**

Description

Klübersynth BHP 72-102 is an innovative, synthetic long-term lubricating grease based on ester oils and perfluorinated polyether oil (PFPE). Its outstanding characteristics are good oil retention at high permanent temperatures and good corrosion protection as well as water resistance - yet another contribution to a longer bearing life and a higher thermal stability compared to conventional lubricants. In tests performed on component test rigs subject to high permanent temperatures up to 200 °C Klübersynth BHP 72-102 offers an extremely long service life.

forms a stable grease collar that serves as a lubricant reservoir resistant to vibration and at the same time helps to protect the bearings against contaminants.

Application notes

Klübersynth BHP 72-102 can be applied by standard metering systems (brush, spatula, grease gun). Ideally, the bearing should be metallically blank. If any anticorrosive fluid has been applied prior to greasing, we recommend checking compatibility with the lubricant.

Application

Klübersynth BHP 72-102 has been designed for the lifetime lubrication of rolling bearings subject to high loads and alternating temperatures ranging from -40 °C to 200 °C. The product is suitable for the lubrication highly loaded rolling bearings in components close to automobile engines, e.g. bearings viscocouplings, belt tensioners, water pumps, fans, servomotors and similar applications. Klübersynth BHP 72-102

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klübersynth BHP 72-102
Cartridge 500 g	+
Can 600 g	+
Bucket, polyethylene (HDPE), 20 kg	+

Product data	Klübersynth BHP 72-102
Article number	094102
Chemical composition, type of oil	PFPE
Chemical composition, type of oil	ester oil
Chemical composition, thickener	polyurea
Chemical composition, solid lubricant	PTFE
Colour space	white
Lower service temperature	-40 °C / -40 °F
Upper service temperature	200 °C / 392 °F



Klübersynth BHP 72-102

High-temperature lubricant with extraordinary anticorrosion properties for lifetime lubrication

Product data	Klübersynth BHP 72-102
Density at 20 °C	approx. 1.30 g/cm ³
Drop point, DIN ISO 2176, IP 396	>= 240 °C
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	240 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	270 x 0.1 mm
Base oil viscosity at 40 °C, calculated value	approx. 130 mm ² /s
Base oil viscosity at 100 °C, calculated value	approx. 20 mm ² /s
Speed factor (n x dm)	approx. 1 000 000 mm/min
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, lower limit value	4 000 mPas
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, upper limit value	8 000 mPas
Corrosion inhibiting properties of lubricating greases, based on DIN 51802, SKF-EMCOR, test duration: 1 week, 3 % NaCl solution	<= 3 corrosion degree
Copper corrosion, DIN 51811, (lubricating grease), 24h/100°C	1 - 100 corrosion degree
Flow pressure of lubricating greases, DIN 51805, test temperature: -40 °C	<= 1 400 mbar
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

Klüber Lubrication München SE & Co. KG / Geisenhausenerstraße 7 / 81379 München / Germany / phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.