



Product Data

Optigear Synthetic 1300

Synthetic Gear Oil

Description

Castrol Optigear Synthetic™ 1300 synthetic gear oils have been developed for the lubrication of highly loaded gears, especially worm gears as well as bearings even when subjected to high operating temperatures.

They differ from gear oils based on mineral oils in the following characteristics: they feature excellent oxidation resistance (even at high temperatures), an outstanding shearing stability and a good viscosity-temperature behaviour. Optigear Synthetic 1300 are synthetic high-temperature gear oils based on polyglycol and are available in the viscosity grades in the data table.

Application

For all types of gears used in severe applications, especially worm gears and circulating systems that lubricate gears, journals, and anti-friction bearings. Recommended for use where oil and reservoir temperatures are unusually high. Optigear Synthetic 1300 gear oils are especially suited for the lubrication of worm gears with steel/bronze combinations. Also for the lubrication of spur, bevel and planetary gears.

Formulated using polyglycol base fluids chosen for their chemical and thermal stability and compatibility with metals and elastomers typically found in machine components. Compatible with most seals except neoprene, butadiene-mixed polymers, polystyrene-butadiene or methacrylate elastomer materials.

Advantages

- In worm gears the coefficients of friction are reduced due to the polyglycol base oils and the wear rates are lowered owing to the optimum additive package
- They feature a high scuffing load capacity and an excellent wear protection: in the FZG test (A/8.3/90) they reach the damage load stage of > 12
- High load-carrying capacity
- Excellent extreme pressure performance
- Long service life
- Suitable for use over a wide range of temperatures

Typical Characteristics

Name	Test Method	Units	1300/ 220	1300/ 460	1300/ 680
ISO Viscosity	-	-	220	460	680
Density @ 15°C / 59°F	ASTM D4052 / ISO 12185	kg/m ³	1070	1075	1070
Kinematic Viscosity @ 40°C / 104°F	ASTM D 445 / ISO 3104	mm ² /s	220	475	680
Kinematic Viscosity @ 100°C / 212°F	ASTM D 445 / ISO 3104	mm ² /s	36,4	76,5	108
Viscosity Index	ASTM D2270 / ISO 2909	-	218	242	250
Flash Point - open cup method	ASTM D92 / ISO 2592	°C	>240	>240	>240
Pour Point	ASTM D97 / ISO 3016	°C	-36	-33	-30
Rust test - distilled water (24 hrs)	ASTM D665A / ISO 7120	Rating	no rust	no rust	no rust
Copper corrosion (3 hrs@100°C/212°F)	ASTM D130 / ISO 2160	Rating	1	1	1
FZG Gear Scuffing test - A/16.6/ 90	ISO 14635-1	Failure load stage	>12	>12	>12
FZG Micropitting test @ 90°C/194°F	FVA 54-7	Failure Load Stage / Micropitting Rating	10/ high ¹	-	-
Foam Sequence I - tendency / stability	ASTM D892 / ISO 6247	ml / ml	50/0	10/0	10/0

Note 1 : Measured on ISO 220 grade

Subject to usual manufacturing tolerances.

Optigear Synthetic 1300

18 Apr 2024

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

<http://msdspds.castrol.com>