
PRODUCT INFORMATION



OKS 2301

Mould Protector, Fluid, Spray





Description

OKS 2301 generates a temporary corrosion protection film for storage and shipping of machine parts with bare metal surfaces.

Applications

- Preservation of bare metal surfaces of all kinds, which are stored for longer periods and are subject to effects of weathering
- Protected parts retain their decorative appearance, as no surface discolouration occurs
- Ideal on-call and storage protection for spare parts with possibility of direction installation

Branches

- Plant and machine (tool) engineering
- Chemical industry
- Rubber and plastic processing
- Paper and packaging industry
- Glass and foundry industry
- Shipbuilding and marine technology
- Logistics
- Municipal services
- Rail vehicle technology
- Iron and steel industry

Advantages and benefits

- Highly effective due to good film-forming properties with lasting water-repelling
- Excellently suited for producing non-slip dry, greenish protective films
- Outstanding corrosion and oxidation protection with lubricating effect
- No removal prior to commissioning, as compatible with all lubricants
- Waterproof and resistant to weathering, suitable for all climate zones
- Can be welded without degreasing
- Easily removable before coating

Application tips

For optimum results clean surfaces, first mechanically and then with OKS 2610/OKS 2611 Universal Cleaner. The surfaces must be metallic bright and dry. Shake well before use. Spray a thin layer evenly from 20-30 cm distance to the prepared surface. Local excess should be avoided. Drying conditions as per the following technical data.

Packaging

400 ml Spray

PRODUCT INFORMATION



OKS 2301

Mould Protector, Fluid, Spray

Technical Data

	Standard	Conditions	Unit	Value
Main components	•		•	
solvent				special boiling point gasoline
solid lubricants	ĺ			synthetic wax
additives				corrosion protection
Application related technica	Il data			
lower operating temperature			°C	-40
upper operating temperature			°C	70
optimal layer thickness	DIN 50 981/50 984	DIN 50 982-2	μm	> 10
surface covering			m²/can	approx. 5
processing temperature			°C	20-25
drying time		20°C	min	6
colour				greenish
density (at 20°C)	DIN EN ISO 3838		g/cm³	0.8
salt spray test	DIN EN ISO 9227	layer thickness 50μm	h	> 1.000

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47 82216 Maisach Phone: +49 (0) 8142 3051 - 500 info@oks-germany.com www.oks-germany.com



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark

Safety data sheet for industrial and commercial users is available for downloading under www.oks-germany.com. Our Customer and Technical service will be pleased to help should you have any further questions.

21.02.2022, En Page 2/2